

CKB™ Nude

Description	Standard	Unit	Values				
Grammage	ISO 536	gsm (g/m ²)	205	230	255	325	345
Thickness	ISO 534	microns (µm)	380	445	495	580	630
Bending Moment Taber 15° MD	TAPPI 489	mNm	12.9	19.2	26.3	49.9	61.1
Bending Moment Taber 15° CD	TAPPI 489	mNm	5.1	7.7	10.5	20.0	24.5
Moisture	ISO 287	%	7.5			8.0	8.5
Smoothness Bendtsen (top side)	SCAN P84:02	ml/min	400				
Smoothness Bendtsen (reverse)	SCAN P84:02	ml/min	700				
Tearing Resistance MD	TAPPI 496	mN	2900	3400	3900	5000	5400
Tearing Resistance CD	TAPPI 496	mN	3300	3800	4300	5700	6200
Cobb 60	ISO 535	g/m ²	30				

FSC® & PEFC certification available upon request

ISO 9001
 ISO 14001
 FSSC 22000
 OHSAS 18001
 ISO 50001