

FiloServe Grease Freeze Kit 11

Description	Standard	Unit	Values		
Weight	T-410	gsm (g/m ²)	250	280	300
Thickness	T-411	microns (µm)	388	440	486
Bending Moment Taber 15° MD	T-489	mNm	13.8	18.7	23.8
Bending Moment Taber 15° CD	T-489	mNm	7.2	9.2	11.2
Ply Bond (avg.)	T-569	J/m ²	150		
Roughness PPS (top side)	T-555	µm	2.00		
Brightness (top side)	T-452	%	85 min		
Whiteness CIE (top side)	T-560	%	85 min		
Surface Strength IGT Pick	ISO 3782 & ISO 3783	m/sec	0.7 min		
COBB 180 seconds (top side)	T-441	g/m ²	50		
COBB 180 seconds (middle)	T-441	g/m ²	100		
COBB 180 seconds (reverse)	T-441	g/m ²	50		
Gloss 75° (top side)	T-480	%	30		
Moisture	T-412	%	7.0		

FSC® certified