

Incada Exel

Description	Standard	Unit	Values								
			200	210	225	235	255	280	300	325	350
Weight	ISO 536	gsm (g/m ²)	200	210	225	235	255	280	300	325	350
Thickness	ISO 534	microns (µm)	310	340	375	400	450	490	540	590	640
Bending Resistance Taber 15° MD	ISO 2493	mNm	8.5	10.6	13.6	15.2	19.6	24.9	30.3	38.7	45.5
Bending Resistance Taber 15° CD	ISO 2493	mNm	3.7	4.6	5.9	6.6	8.5	10.8	13.2	16.8	19.8
Whiteness (printing side)	ISO 11475	%	120								
Whiteness (reverse)	ISO 11475	%	97								
Brightness (printing side)	ISO 2470	%	91.5								
Brightness (reverse)	ISO 2470	%	86.0								
Board Gloss 75°	ISO 8254-1	%	50								
Cobb 60	ISO 535	g/m ² /60 sec	30								

FSC® certified

ISO 9001
 ISO 14001
 ISO 45001
 ISO 50001