

Proxima Plus

Description	Specification	Unit	Technical detail						
			215	235	250	270	295	325	350
Basis Weight	ISO 536	gsm (g/m ²)	215	235	250	270	295	325	350
Thickness	ISO 534	microns (µm)	350	385	420	460	510	560	610
Stiffness (15°) CD	ISO 2493	mNm	5.32	7.05	8.31	10.8	15.2	17.8	24.5
Stiffness (15°) MD	ISO 2493	mNm	9.48	12.6	15.8	20.9	29.3	32.2	40.0
Moisture	ISO 287	%	7.0						
Roughness - top	ISO 8791-4	µm	1.5						
Brightness D65/10 - top	ISO 2470-1	%	82.0						
Gloss - top	Tappi T480	%	40						
IGT - top	ISO 8254-1	m/s	1.20						
Cobb 180s - top/middle/back	ISO 535	g/m ²	60						
Scott Plybonding	Tappi T569	J/m ²	130						
Squareness	GB/T 451.1	mm	2.0						
Size Deviation	GB/T 451.1	mm	2.0						