

Tambrite™ HS

Description	Standard	Unit	Values										
Weight	ISO 536	gsm (g/m ²)	200	210	220	230	240	250	260	270	285	310	335
Thickness	ISO 534	microns (µm)	350	375	400	420	440	460	480	500	540	600	650
Bending Moment Taber 15° MD	ISO 2493	mNm	9.0	10.7	12.4	14.3	16.2	18.1	20.5	23.0	27.6	35.5	43.7
Bending Moment Taber 15° CD		mNm	5.0	5.9	6.8	7.8	8.8	9.8	11.0	12.3	14.6	18.5	22.4
Moisture	ISO 287	%	8.0								8.5		9.0
ISO Brightness C/2° (top side)	ISO 2470-1	%	86										
Surface Smoothness PPS 10 (top side)	ISO 8791-4	µm	1.2										
Scott Bond	T-569	J/m ²	130										
Robinson Chocolate Test	EN 1230-2		max. 0.5 for one year storage in reels/pallets										

FSC® certified

ISO 9001
 ISO 14001
 FSC 22000
 OHSAS 18001
 ISO 50001