

Target Executive

Description	Standard	Unit	Values		
Grammage	ISO 536	gsm (g/m²)	80	90	100
Thickness	ISO 534	microns (µm)	108	112	120
Whiteness	ISO 11475	CIE	169	169	169
Opacity	ISO 2471	%	95	96	97
Moisture	ISO 287	%	4.0	4.0	4.0
Bendtsen Roughness	ISO 8791/2	ml/min	160	140	100
Bulk Thickness	ISO 536	µm/g.m-2	1.35	1.24	1.20

Product Certifications

FSC®  
EU Ecolabel

Mill Certifications

ISO 9001  
ISO 14001