

Twin Kraft

Description	Standard	Unit	Values				
Weight	ISO 536	gsm (g/m ²)	300	340	400	450	500
Thickness	ISO 534	microns (µm)	420	490	590	660	738
Bending Moment Taber 15° MD	ISO 2493	mNm	20	31	47	52	57
Bending Moment Taber 15° CD	ISO 2493	mNm	6	9	15	17	20

FSC® certified