

Uniboard-S

Description	Standard	Unit	Values										
			250	280	300	320	350	380	400	425	450	500	550
Weight	ISO 536	gsm (g/m ²)	250	280	300	320	350	380	400	425	450	500	550
Thickness	ISO 534	microns (µm)	310	350	380	410	450	490	510	545	580	640	710
Stiffness L&W 5° MD	DIN 53121	mNm	14.7	20.2	24.5	30.1	37.6	47.2	53.6	63.1	72.5	94.8	119.7
Stiffness L&W 5° CD	DIN 53121	mNm	5.5	7.6	9.1	11.3	14.6	18.7	21.5	26.1	30.6	41.1	50.7
Stiffness Taber 15° MD	T-489	mNm	8.4	11.1	12.9	15.3	18.8	23.3	26.5	30.9	35.3	45.3	56.1
Stiffness Taber 15° CD	T-489	mNm	2.9	3.8	4.3	5.4	7.1	8.7	10.2	12.5	14.9	20.0	24.5
Brightness	ISO 2470-02	%	81										
Cobb 60"		g/m ²	50										

ISO 9001
ISO 50001