

CYBER XL PAC

GC2 • GREASE FREEZE

August 2019



Data Sheet	Specification	Unit	Target		
			250	280	300
Grammage	Tappi T 410	g/m2	250	280	300
Thickness	Tappi T 411	μm	388	440	486
Bending resistance (L&W) MD	Tappi T 556	mN	280	379	483
Bending resistance (L&W) CD	Tappi T 556	mN	146	186	227
Bending resistance (L&W) GM	Tappi T 556	mN	202	266	331
Ply Bond	Tappi T 569	J/m ²	150 min		
Roughness PPS Top	Tappi T 555	μm	2.00		
Brightness Top	Tappi T 452	%	85 min		
Whiteness CIE Top	Tappi T 560	%	85 min		
Surface Strength IGT Pick Top	ISO 3782 & 3783		0.7 min		
Cobb (180 seconds) Top	Tappi T441	g/m2	50		
Cobb (180 seconds) Middle	Tappi T441	g/m2	100		
Cobb (180 seconds) Bottom	Tappi T441	g/m2	50		
Gloss 75° Top	Tappi T 480	%	30 min		
Moisture	Tappi T 412	%	7.0		