

Accurate™

Description	Standard	Unit	Values												
			215	230	245	265	275	290	305	325	350	375	400	425	450
Weight	ISO 536	gsm (g/m ²)	215	230	245	265	275	290	305	325	350	375	400	425	450
Thickness	EN 20534	microns (µm)	340	370	400	440	460	490	520	560	615	670	725	780	840
Stiffness Taber 15° MD	DIN 53121	mNm	7.7	9.8	11.9	15.0	16.7	19.7	22.7	27.4	34.1	41.9	50.8	60.8	71.8
Stiffness Taber 15° CD	DIN 53121	mNm	3.6	4.9	6.0	7.6	8.5	10.0	11.6	14.1	17.6	21.6	26.3	31.4	37.1
Brightness Elrepho (top side)	ISO 2470-2	%	90												
Smoothness PPS (top side)	ISO 8791-4	µm	1.0												
Gloss 75°	ISO 8254	%	45												
Cobb 180 sec (top side)	ISO 535	g/m ²	60												
Cobb 180 sec (reverse side)	ISO 535	g/m ²	50												

ISO 9001
 ISO 14001
 EN 15593 (HACCP)
 ISO 50001