

Adestor MC Gloss Removable

Face material - Gloss 80

Data sheet	Specification	Unit	Values
Grammage	ISO 536	gsm (g/m ²)	80
Thickness	ISO 534	microns (µm)	67
Bekk Smoothness	ISO 5627	s	≥950
Brightness ISO	ISO 2470-2	%	93
Whiteness CIE	ISO 11475	%	117
Paper Gloss 75°	ISO 8254-2	%	66
Opacity	ISO 2471	%	85
Tensile Strength MD	ISO 1924-2	kN/m	4.4
Tensile Strength MD/CD	ISO 1924-2	kN/m	2.5

Backing material - Kraft White 90

Data sheet	Specification	Unit	Values
Grammage	ISO 536	gsm (g/m ²)	90
Thickness	ISO 534	microns (µm)	90
Tensile Strength MD/CD	ISO 1924-2	kN/m	5.2/2.6

Adhesive - RA678

Data sheet	Specification	Unit	Values
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	1.7
Tack (Quick Stick stainless steel)	FTM 9	N	1.2
Shear (1kg in ² /glass)	FTM 8	min	120
Minimum labelling temperature		°C	+5
Minimum service temperature		°C	-20
Maximum service temperature		°C	+80

Product Certifications

FSC®

Mill Certifications

ISO 9001

ISO 45001