

Aegle® Pro

Description	Standard	Unit	Values													
			180	190	200	210	225	235	245	260	270	290	310	340	360	380
Grammage	ISO 536	gsm (g/m ²)	180	190	200	210	225	235	245	260	270	290	310	340	360	380
Thickness	ISO 534	microns (µm)	305	325	350	375	400	425	450	480	500	550	600	650	695	740
Bending moment Taber 15° MD	ISO 2493	mNm	6.5	8.3	10.3	12.4	14.4	16.4	18.6	22.0	24.6	30.5	36.4	45.0	52.0	61.0
Bending moment Taber 15° CD	ISO 2493	mNm	3.0	3.9	5.0	5.9	7.2	8.2	9.3	11.0	12.3	15.5	18.5	22.0	27.0	31.0
Moisture	ISO 287	%	7.8	7.8	8.0	8.0	8.0	8.0	8.0	8.5	8.5	8.7	9.0	9.0	9.0	9.0
ISO Brightness D65 top	ISO 2470	%	87													
Surface Smoothness PPS10	ISO 8791-4	µm	1.2													
Gloss 75°	ISO 8254-1	%	45													
Cobb 3 min top/back	ISO 535	g/m ²	50													
Scott Bond	Tappi T569	J/m ²	150													

FSC® certified

ISO 9001
ISO 14001