

Aegle® White

Description	Standard	Unit	Values											
			200	210	220	235	245	255	270	280	290	305	330	355
Grammage	ISO 536	gsm (g/m ²)	200	210	220	235	245	255	270	280	290	305	330	355
Thickness	ISO 534	microns (µm)	285	305	325	355	375	395	425	445	470	500	550	600
Bending moment Taber 15° MD	ISO 2493	mNm	6.0	7.7	9.7	12.0	14.0	16.0	19.0	20.8	23.3	27.0	34.0	41.0
Bending moment Taber 15° CD	ISO 2493	mNm	3.4	4.0	4.8	6.0	6.8	7.8	9.1	10.0	11.2	13.0	16.0	20.0
Moisture	ISO 287	%	8.0	8.0	8.0	8.0	8.0	8.5	8.5	8.7	8.7	9.0	9.0	9.0
ISO Brightness D65 top	ISO 2470	%	91	91	91	91	91	91	91	91	91	91	91	91
ISO Brightness D65 back	ISO 2470	%	86	86	86	86	86	86	86	86	86	86	86	86
Surface Smoothness PPS10	ISO 8791-4	µm	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
Gloss 75°	ISO 8254-1	%	45	45	45	45	45	45	45	45	45	45	45	45
Cobb 3 min top/back	ISO 535	g/m ²	50	50	50	50	50	50	50	50	50	50	50	50
Scott Bond	Tappi T569	J/m ²	130	130	130	130	130	130	130	130	130	130	130	130

FSC® certified

ISO 9001
ISO 14001