

Ambassador Laid

| Description | Standard | Unit | Values |
|-------------------------|----------|-------------------------|--------|
| Grammage | | gsm (g/m ²) | 100 |
| Thickness | | microns (µm) | 140 |
| Burst | | kPa | 150 |
| Cobb (1 min) | | g/m | 25 |
| Bendtsen Roughness | | ml/min | 400 |
| Dennison Wax Pick/Clear | | ml/min | 12 |
| Moisture | | % | 6 |

Product Certifications

FSC®
 Toy safe (94/62/CE & EN71-3)
 CONEG compliant
 REACH compliant

Mill Certifications

ISO 9001
 ISO 14001
 ISO 45001
 ISO 50001