

## WestRock Crescendo® C2S

Description	Standard	Unit	Values						
Weight	T-410	gsm (g/m <sup>2</sup> )	220	260	295	320	345	375	440
Thickness	T-411	microns (µm)	254	305	356	406	457	508	610
Stiffness Taber 15° MD	ISO 2439	mNm	5.9	9.8	13.2	19.1	24	30.9	46.1
Stiffness Taber 15° CD	ISO 2439	mNm	3.1	4.9	6.9	9.3	12.4	16.2	23.6
Moisture	T-412	%	4.8						
Parker Print	ISO 8791	µm	1.0						
ISO Brightness (coated side)	ISO 2470	%	91						
GE Brightness (coated side)	T-452	%	92						
CIE Whiteness (coated side)	ISO 11475	%	122						

**PEFC certified**

ISO 9001