

WestRock CustomKote®

Description	Standard	Unit	Values								
Weight	T-410	gsm (g/m ²)	290	330	360	390	415	450	485	520	555
Thickness	T-411	microns (µm)	356	406	457	508	559	610	660	711	762
Moisture	T-412	%	7.0						7.2		
Stiffness Taber 15° MD	T-489	mNm	13.7	19.6	27.0	34.3	43.1	53.4	63.7	74.5	85.3
Stiffness Taber 15° CD	T-489	mNm	6.9	9.8	13.7	17.2	20.6	25.0	30.4	36.3	41.7
GE Brightness (top side)	T-452	%	78								
Gloss	T-480	%	50								
Parker Print	T-555	µm	1.7								
Smoothness Sheffield	T-538	ml/min	80	90	115	140	145		165		
Colour Hunter	T-524	L-a-b	0.7								

PEFC certified

ISO 9001