

## Cyber Fusion

Description	Standard	Unit	Values	
Weight	T410	gsm (g/m <sup>2</sup> )	475	615
Thickness	T411	microns (µm)	750	1000
Bulk		cm <sup>3</sup> /g	1.58	1.63
Ply Bond (avg.)	T-569	J/m <sup>2</sup>	150	
Moisture	T-412	%	8.5	

### Product Certifications

FSC®  
Food safe

### Mill Certifications

ISO 9001  
ISO 14001  
OHSAS 18001  
BRC