

## Cyber Premium

Description	Standard	Unit	Values							
			352	398	437	486	540	594	648	684
Thickness	T-411	microns (µm)	352	398	437	486	540	594	648	684
Weight	T-410	gsm (g/m <sup>2</sup> )	220	240	260	270	300	330	360	380
Stiffness Taber 15° MD	T-489	mNm	9.9	12.7	16.7	23.5	32.5	40.7	52.8	59.8
Stiffness Taber 15° CD	T-489	mNm	5.1	6.3	8.4	11.8	16.2	20.3	26.4	29.9
Ply Bond (avg.)	T-569	J/m <sup>2</sup>	150							
Roughness PPS (top side)	T-555	µm	2.1			2.3				
Brightness ISO (top side)	T-452	%	85 min							
Whiteness CIE (top side)	T-560	%	85 min							
Surface Strength IGT Pick (top side)	ISO 3782 & ISO 3783	m/sec	0.7 min							
Gloss 75° (top side)	T-480	%	35							
Moisture	T-412	%	6.0-7.5							

**FSC® certified**