

Enduro Premium

Data sheet	Specification	Unit	Values	
Grammage	ISO 536	gsm (g/m ²)	160	280
Thickness	ISO 534	microns (µm)	135	250
Bending stiffness MD	ISO 2493-1	mN	280	1200
Bending stiffness CD	ISO 2493-1	mN	100	500
Tensile strength MD	ISO 1924	N/15mm	140	200
Tensile strength CD	ISO 1924	N/15mm	80	140
ISO Brightness	ISO 2470-1	%	85	85
Whiteness, CIE, D65/10°	ISO 11475		110	115
Opacity	ISO 2471	%	93	98

Product Certifications

FSC®

Mill Certifications

ISO 9001

ISO 14001

ISO 14001

ISO 50001