

WestRock EnShield® Natural Kraft

Description	Standard	Unit	Values				
Grammage	T-410	GSM	283	322	351	381	410
Thickness	T-411	micron	356	406	457	508	559
Moisture	T-412	%	7.0	7.0	7.0	7.0	7.0
ZDT	T-541	psi	35	35	35	35	35
Stiffness Taber 15° - MD	T-489	mNm	13.7	19.6	27.0	34.3	43.1
Stiffness Taber 15° - CD	T-489	mNm	6.9	9.8	13.7	17.2	20.6
Oil & Grease Resistance (OGR)	T-559	3M Kit	12	12	12	12	12

PEFC certified

ISO 9001
ISO 14001