

## FiloServe Grease Freeze Kit 11

Description	Standard	Unit	Values			
Thickness	T-411	microns (µm)	388	440	486	518
Weight	T-410	gsm (g/m <sup>2</sup> )	250	280	300	320
Bending Moment Taber 15° MD	T-489	mNm	13.8	18.7	23.8	28.8
Bending Moment Taber 15° CD	T-489	mNm	7.2	9.2	11.2	14.2
Ply Bond (avg.)	T-569	J/m <sup>2</sup>	150			
Roughness PPS (top side)	T-555	µm	2.00			
Brightness (top side)	T-452	%	85 min			
Whiteness CIE (top side)	T-560	%	85 min			
Surface Strength IGT Pick	ISO 3782 & ISO 3783	m/sec	0.7 min			
COBB 180 seconds (top side)	T-441	g/m <sup>2</sup>	50			
COBB 180 seconds (middle)	T-441	g/m <sup>2</sup>	100			
COBB 180 seconds (reverse)	T-441	g/m <sup>2</sup>	50			
Gloss 75° (top side)	T-480	%	30			
Moisture	T-412	%	7.0			

### Product Certifications

FSC®  
Food safe

### Mill Certifications

ISO 9001  
ISO 14001  
ISO 45001  
BRC