

Hermicoat WR

Description	Standard	Unit	Values									
			280	300	320	340	350	360	380	400	425	450
Weight	ISO 536	gsm (g/m ²)	280	300	320	340	350	360	380	400	425	450
Thickness	ISO 534	microns (µm)	380	410	440	465	480	495	520	550	580	615
Stiffness Taber 15° MD	ISO 2493	mNm	11.8	14.1	16.7	19.5	21.0	22.3	24.6	28.9	33.4	37.9
Stiffness Taber 15° CD	ISO 2493	mNm	4.7	5.7	6.9	8.2	8.8	9.7	11.0	12.6	15.2	17.5
Brightness (top side)	ISO 2470	%	84									
Cobb 60"	ISO 535	g/m ²	60									

ISO 9001
ISO 50001