

Incada Silk

Description	Standard Used	Unit	Value						
			325	365	405	445	485	540	590
Thickness	ISO 534	micron	325	365	405	445	485	540	590
Grammage	ISO 534	gsm	220	240	260	280	300	325	350
Bending Resistance Taber 15° MD	ISO 2493	mNm	9.8	13.1	16.9	21.3	26.3	33.0	40.2
Bending Resistance Taber 15° CD	ISO 2493	mNm	4.5	5.9	7.7	9.7	12.0	15.0	18.2
Whiteness (printing side)	ISO 11475	%	120	120	120	120	120	120	120
Whiteness (reverse)	ISO 11475	%	114	114	114	114	114	114	114
Brightness (printing side)	ISO 2470	%	9.15	9.15	91.5	91.5	91.5	91.5	91.5
Brightness (reverse)	ISO 2470	%	90.5	90.5	9	90.5	90.5	90.5	90.5
Board Gloss 75°	ISO8254-1	%	50	50	50	50	50	50	50
Cobb	ISO 535	g/m ² 60 sec	30	30	30	30	30	30	30

FSC® certified

ISO 9001
 ISO 14001
 ISO 45001
 ISO 50001