

Invercote Creato

Description	Standard	Unit	Values							
			220*	240*	260*	280*	300*	350*		400*
Grammage	ISO 536	gsm (g/m ²)	220*	240*	260*	280*	300*	350*		400*
Thickness	ISO 534	microns (µm)	230	260	290	315	345	415		485
Opacity	ISO 2471	%	96.8	97.3	97.7	98.1	98.5	99.0		99.5
Whiteness	ISO 11475	%	127	127	127	127	127	127		127
Brightness	ISO 2470	%	94	94	94	94	94	94		94
Surface Roughness	ISO 8791-4	µm	1.2	1.2	1.2	1.2	1.2	1.2		1.2
Board Gloss 75°	ISO8254-1	%	40	40	40	40	40	40		40
Cobb	ISO 535	g/m ² 60s	30	30	30	30	30	30		30
Bending Stiffness L&W 5° - MD	ISO 5628	mNm	10.1	13.5	18.7	24.3	30.1	47.8		72.4
Bending Stiffness L&W 5° - CD	ISO 5628	mNm	4.8	6.4	8.9	11.6	14.4	22.8		33.6
Bending Taber 15° - MD	ISO 2493	mNm	5.2	7.2	9.8	12.8	14.5	25.1		39.6
Bending Taber 15° - CD	ISO 2493	mNm	2.4	3.4	4.6	5.9	7.3	12.1		18.1

FSC® certified

ISO 9001
 ISO 14001
 OHSAS 18001
 ISO 50001
 HP Indigo Certified (not 400gsm)