

WestRock KraftPak™ Evadale

Description	Standard	Unit	Value							
Thickness	T-411	microns (µm)	381	432	457	508	559	610	660	
Weight	T-410	gsm (g/m ²)	258	288	302	332	356	380	410	
Moisture	T-412	%	5.8							
Stiffness Taber 15 - MD	T-489	mNm	11.8	16.2	19.6	26.5	30.9	38.2	45.1	
Stiffness Taber 15 - CD	T-489	mNm	5.4	6.4	8.3	10.8	14.2	17.2	21.1	
Cobb - Top	T-441	g/m ²	40							
Cobb - Bottom	T-441	g/m ²	40							
ZDT	T-541	kPa	150	380			340		310	
Sheffield - Top	T-538	SU	380	390	400	405	390	395	400	
Gurley Porosity	T-460	sec/100ml	15				10			
Tear	T-414	MD	4.9	5.7	5.9	6.1	6.9	7.3	8.2	

Product Certifications

PEFC
ISEGA
Food safe

Mill Certifications

ISO 9001