

Magno Satin (formerly GalerieArt Satin)

Data Sheet	Specification	Unit	Target													
			90	100	115	130	150	170	200	250	300	350	400	450	400	450
Grammage	ISO 536	gsm	90	100	115	130	150	170	200	250	300	350	400	450	400	450
Thickness	ISO 534	µm	74	82	94	107	125	141	168	225	282	347	412	477	412	477
Brightness (illuminant D65/10°)	ISO 2470-2	%	100	100	100	100	100	100	100	100	100	100	100	100	100	101
CIE Whiteness (D65/10°)	ISO 11475	%	127	127	127	127	127	127	127	127	127	127	127	127	127	128
Opacity	ISO 2471	%	91	92.5	94.5	95	96.5	97.5	98	98.5	99	99.5	99.5	99.5	99.5	99.5
Gloss TAPPI 75°	ISO 8254-1	%	38	38	38	38	38	38	38	38	38	38	38	22	38	25
Roughness PPS	ISO 8791-4	µm	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.5	1.5	1.5	1.5	1.5	1.5	2.0
Bulk	ISO 534	cm³/g	0.82	0.82	0.82	0.82	0.83	0.83	0.84	0.90	0.94	0.99	1.03	1.06	1.03	1.06
Relative Humidity (23°C)	TAPPI 502	%	50	50	50	50	50	50	50	50	50	50	50	50	50	50

FSC® certified

ISO 9001
 ISO 14001
 OHSAS 18001
 ISO 50001