

Multiboard® EcoFrost

Description	Standard	Unit	Values							
			280	300	325	350	375	400	425	450
Weight	ISO 536	gsm (g/m ²)	280	300	325	350	375	400	425	450
Thickness	ISO 534	microns (µm)	375	405	445	480	515	550	585	630
Bending Moment Taber 15° MD	T-489	mNm	13.3	16.2	20.3	24.9	29.9	36.0	43.0	50.7
Bending Moment Taber 15° CD	T-489	mNm	4.8	5.8	7.2	8.9	10.9	13.0	15.0	17.9
Brightness R457	ISO 2470	%	79							
Whiteness D65/10	ISO 11475	%	84							
Cobb 180 (reverse side)	ISO 535	g/m ²	40							

ISO 9001
ISO 14001