

Multiboard® EcoFrost

Description	Standard	Unit	Values							
			375	405	445	480	515	550	585	630
Thickness	ISO 534	microns (µm)	375	405	445	480	515	550	585	630
Weight	ISO 536	gsm (g/m ²)	280	300	325	350	375	400	425	450
Bending Moment Taber 15° MD	T-489	mNm	13.3	16.2	20.3	24.9	29.9	36.0	43.0	50.7
Bending Moment Taber 15° CD	T-489	mNm	4.8	5.8	7.2	8.9	10.9	13.0	15.0	17.9
Brightness R457	ISO 2470	%	79							
Whiteness D65/10	ISO 11475	%	84							
Cobb 180 (reverse side)	ISO 535	g/m ²	40							

Product Certifications

ISEGA
Food safe

Mill Certifications

ISO 9001
ISO 14001