

## Norcoppy 100% Recycled

Description	Standard	Unit	Values
Grammage	AS/NZS 1301.450s	gsm (g/m <sup>2</sup> )	80
Thickness	AS/NZS 1301.426s	microns (µm)	107
Moisture	AS/NZS 1301.457s	%	4.5
Filler	AS/NZS 1301.418s	%	20
Roughness (Bendtsen)	AS/NZS 1301.439s	ml/min	160
Porosity (Bendtsen)	AS/NZS 1301.440s	ml/min	1700
Cobb, 1 min (multi sheet)	AS/NZS 1301.411s	g/m <sup>2</sup>	35
Brightness (UV Inc) D65/10°	AS/NZS 1301.462s		106
Opacity	AS/NZS 1301.454s	%	91.5
CIE Whiteness D65/10°	ISO 11475		155
Dirt EBA	Tappi 563	ppm	20

**FSC® certified**

ISO 9001  
ISO 14001  
Carbon Offset