

WestRock PrintKote®

| Description | Method | Unit | Values | | | | | |
|-----------------------------|--------|-------------------------|--------|------|------|------|------|------|
| | | | | | | | | |
| Basis Weight | T-410 | gsm (g/m ²) | 265 | 295 | 325 | 345 | 405 | 460 |
| Thickness | T-411 | microns (µm) | 356 | 406 | 457 | 508 | 610 | 711 |
| Stiffness Taber 15° MD | T-489 | mNm | 11.8 | 16.7 | 21.6 | 27.5 | 43.1 | 53.9 |
| Stiffness Taber 15° CD | T-489 | mNm | 5.9 | 9.3 | 11.8 | 15.2 | 22.6 | 28.4 |
| Moisture | T-412 | % | 5.3 | 5.6 | 5.6 | 5.6 | 5.6 | 5.6 |
| Internal Bond | T-569 | J/m ² | 147 | 147 | 147 | 158 | 168 | 168 |
| GE Brightness (coated side) | T-452 | % | 86 | | | | | |
| Parker Print (coated side) | T-555 | µm | 1.0 | 1.1 | 1.1 | 1.2 | 1.2 | 1.2 |
| ZDT | T-541 | kPa | 324 | 310 | 276 | 276 | 276 | 276 |

PEFC certified

ISO 9001