

Sappi Raw

Data sheet	Specification	Unit	Technical detail						
			115	135	150	170	200	250	300
Grammage	ISO 536	gsm (g/m ²)	115	135	150	170	200	250	300
Thickness	ISO 534	microns (µm)	138	162	180	204	240	300	360
Brightness D65/10°	ISO 2470-2	%	104	104	104	104	104	104	104
CIE Whiteness D65/10°	ISO 11475	%	144	144	144	144	144	144	144
Opacity	ISO 2471	%	96	97	98	99	>99	>99	>99
Roughness Bendtsen	ISO 8791-2	ml/min	<450	<450	<450	<450	<450	<500	<550
Bulk	ISO 534	cm ³ /g	1.20	1.20	1.20	1.20	1.20	1.20	1.20
Relative Humidity	TAPPI 502	%	50	50	50	50	50	50	50

FSC® certified

ISO 9001
 ISO 14001
 ISO 50001
 ISO 45 001