

Rey[®] Copy

Description	Standard	Unit	Values
Substance	ISO 536	gsm (g/m ²)	80
Thickness	ISO 534	microns (μm)	104
Bulk	ISO 534	cm ³ /g	1.31
Smoothness - Bendtsen	ISO 8791	ml/min	200
Whiteness	ISO 11475	CIE	146
Opacity	ISO 2471	%	89
Stiffness - SM	ISO 2493	m/Newton	110
Stiffness - ST	ISO 2493	m/Newton	45

FSC[®] certified

ISO 9706
EU EcoLabel
Colorlok Technology