

Rochperle GC2 Kit 8

Description	Standard	Unit	Values			
Weight	ISO 536	gsm (g/m ²)	230	250	275	300
Thickness	ISO 534	microns (µm)	375	425	475	515
Stiffness Taber 15° MD		mNm	11.3	15.3	20.5	25.5
Stiffness Taber 15° CD		mNm	4.8	6.4	8.7	11.0
Stiffness L&W 5° MD	DIN 53 121	mNm	21.2	28.6	38.3	47.7
Stiffness L&W 5° CD	DIN 53 121	mNm	9.2	12.3	16.7	21.2
Brightness (top side)	ISO 2470	%	90			
Cobb 3 min (top and reverse)	ISO 535	g/m ²	50			
Robinson Test (taint)	NF EN 1230-2	0-4 scale	<1			

ISO 9001