

Serviliner

| Description | Standard | Unit | Values | | | | | |
|-------------------------|------------|-------------------------|--------|-----|-----|-----|-----|-----|
| Weight | ISO 536 | gsm (g/m ²) | 160 | 180 | 195 | 210 | 230 | 250 |
| Thickness | ISO 534 | microns (µm) | 170 | 200 | 219 | 237 | 262 | 288 |
| Strength SCT CD | ISO 9895 | kN/m | 2.4 | 2.5 | 2.8 | 3.0 | 3.3 | 3.6 |
| Burst Strength | ISO 2759 | kPa | 280 | 320 | 340 | 360 | 385 | 410 |
| Roughness | ISO 8791-2 | ml/min | 45 | | | | | |
| Cobb 60" (reverse side) | ISO 535 | g/m ² | 60 | | | | | |
| Brightness (top side) | ISO 2470-2 | % | 84 | | | | | |

ISO 9001
ISO 14001