

Titan Matt

Description	Standard	Unit	Values																					
			80	90	95	100	105	113	118	128	135	140	148	157	170	180	200	218	230	235	250	270	300	350
Weight		gsm (g/m ²)	80	90	95	100	105	113	118	128	135	140	148	157	170	180	200	218	230	235	250	270	300	350
Thickness	Tappi 411	microns (µm)	71	80	85	90	95	102	107	116	124	130	145	155	161	177	198	229	230	235	257	283	320	373
Brightness	Tappi 525	%	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90	90
Whiteness	Tappi 560	%	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113	113
Opacity	Tappi 519	%	87	89	90	91	92	93	94	94	94	96	96	96	97	97	97	97	98	98	98	98	98	99
Gloss	Tappi 480	%	37	37	37	37	37	37	37	37	37	37	37	37	37	37	38	38	38	38	38	38	38	38
Roughness	Tappi 555	µm	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.7	2.7	2.7	2.7	2.7	2.7	2.7	2.7

Product Certifications
FSC®

Mill Certifications
ISO 9001
ISO 14001