

Vision Superior

| Description | Unit | Values | | | | | | | | | | |
|---------------------|-------------------------|--------|------|------|------|------|------|------|------|------|------|------|
| Grammage | gsm (g/m ²) | 100 | 120 | 135 | 160 | 200 | 250 | 300 | 350 | 400 | 450 | 500 |
| Caliper | microns (µm) | 128 | 153 | 176 | 208 | 260 | 325 | 390 | 450 | 512 | 576 | 640 |
| CIE Whiteness - D65 | % | 170 | 170 | 170 | 170 | 170 | 170 | 170 | 170 | 170 | 170 | 170 |
| Bulk | cm ³ /g | 1.28 | 1.28 | 1.2 | 1.31 | 1.30 | 1.30 | 1.30 | 1.30 | 1.30 | 1.30 | 1.30 |
| Opacity | % | 96 | 96 | 98.5 | 99 | 99 | 99.5 | 100 | 100 | 100 | 100 | 100 |
| Smoothness Bendtsen | ml/min | 200 | 200 | 200 | 200 | 200 | 200 | 200 | 200 | 200 | 350 | 350 |

Product Certifications

FSC® certified

Mill Certifications

ISO 9001

ISO 14001