

## X-Brite

Description	Standard	Unit	Values
Thickness	ISO 534	microns (µm)	96
Moisture Content	ISO 287	%	4.0-5.0
Opacity	ISO 2471	%	90.0
Roughness	ISO 8791	ml/min	250
Stiffness Bending 15° MD	ISO 2493	mNm	0.27
Stiffness Bending 15° CD	ISO 2493	mNm	0.12
Brightness	ISO 2470	%	95
CIE Whiteness	ISO 11475	%	160

### Product Certifications

PEFC  
ISO 9706

### Mill Certifications

ISO 9001  
ISO 14001