

Zenith GC1

Description	Standard	Unit	Technical Detail								
Basis Weight	ISO 536	gsm (g/m ²)	215	235	250	270	295	325	350	380	
Thickness	ISO 534	microns (µm)	305	355	380	410	460	510	560	610	
Stiffness Taber MD	ISO 2493	mNm	6.5	10.0	13.0	16.0	22.5	28.5	35.0	40.0	
Stiffness Taber CD	ISO 2493	mNm	3.3	5.0	6.8	8.2	11.0	14.6	17.0	20.0	
Moisture	ISO 287	%	6.5					7.0			
PPS Top	ISO 8791-4	µm	1.40								
Brightness Top	ISO 2470-2	%	91.5								
Gloss 75° Top	ISO 8254-1	%	45								
IGT Blister Top	ISO 3783	m/s	1.50								
Cobb Test 60 Top	ISO 535	g/m ²	40.0								
Ply Bonding	TAPPI 569	J/m ²	130								