

PRODUCT DATA

FASSON®

FASSON® Dry Toner Films

Issued December 2023

Introduction

A self-adhesive film sheet product for digital printing on dry toner machines.

Description

Face: Laser PET - transparent, white, or silver polyester films with matt or gloss finish and a toner receptive surface.

PO Laser - white, matt polyethylene film with a toner receptive surface.

PP Laser - biaxially oriented, white, matt polypropylene film with a toner receptive surface.

Availability

	Adhesive ↻	Permanent	Extra Permanent
Backing ↻			
No cracklines		x	x

Printing & Conversion

All products are specifically engineered for use on the Dry Toner sheet-fed presses. Each face material gives excellent toner key (no pre-treatment needed). Stable constructions ensure problem-free runability.

Before applying the label, the surface must be clean, dry and grease-free (see Technical bulletin 7.1).

Features:

Excellent layflatness, enabling high speed printing using the advantages of full-colour DIGITAL printing such as: short runs, personalisation etc. All adhesives are specifically developed for applications on rough and apolar surfaces.

Recommendations for use

Multi-colour-, identification-, mailing (addressing/shipping)-, carton-, packaging-, inventory-, pricing-, barcode labels. Promotional-, seasonal- and theme- stickers. Suitable for flat or curved surfaces. For indoor and outdoor use.

General

Shelf life: 2 years stored at 20°C / 55% R.H.

For information regarding EHS regulation, please visit our website under downloads “Technical bulletins“ TB 7.8 Product Compliance Fasson Offset” and for technical guidance “Technical bulletins“ – Offset printing.

PRODUCT CHARACTERISTICS

Physical properties

Face	Laser PET White Matt	Laser PET White Gloss	Laser PET Transp. Gloss	Laser PET Silver Matt	PO Laser	PP Laser
Basis weight:	82 g/m ²	70 g/m ²	70 g/m ²	80 g/m ²	115 g/m ²	90 g/m ²
Caliper:	61 micron	51 micron	51 micron	55 micron	178 micron	92 micron

Adhesive

Permanent	General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces.
Extra Permanent	Acrylic super-permanent adhesive with high tack. For difficult surfaces such as wood, some cardboards, and plastics such as HDPE, PP, PET, and PVC.

	Permanent	Extra Permanent
Adhesion (N/25mm) (FTM 1 peel 180° 20'/stainless steel)	15.4	17.2
Tack (N) (FTM 9 on stainless steel)	10.3	11
Minimum application temperature	+5	+5
Service temperature range after 24 hrs (°C)	+80	+80
Resistance to cold (°C) ¹⁾ down to	-20	-20

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Backing

No cracklines: A bleached one-side-coated white kraft, especially designed for sheet products, featuring minimal moisture sensitivity.

Laser PET

Basis weight:	120 g/m ²	ISO 536
Caliper:	118 micron	ISO 534

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.
All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>
Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.