PRODUCT DATA



FASSON[®] HG White DI-OF FSC® Certified

Issued December 2023

Introduction Qualified self-adhesive material for INDIGO DIGITAL presses. Optimized to secure excellent runability and print performance.

Description

Availabilitu

Face:

Premium-quality cast-coated woodfree paper, mirror finish, white. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Availability Adhesive Ə Backing U	Permanent
Crack-Back [®] Plus (diagonal cracklines)	x

Printing & Conversion

This product is specifically engineered for use on the INDIGO DIGITAL sheet-fed press. The face material gives good toner key (no pre-treatment needed). Stable construction ensures problem-free runability. Before applying the label, the surface must be clean, dry and greasefree. Also printable in conventional offset.

Features:

Qualified material ensures problem free conversion. The unique Crack-Back[®] Plus: backing removal system with diagonal scored lines facilitates creating lay-outs, conversion, and application of the label.

Recommendations for use

Multi-colour quality labels, promotional and collectable stickers using the advantages of full-colour DIGITAL printing such as: short runs, personalization etc. For indoor use.

General

Shelf life: Total caliper (±10 %): 2 years stored at 20°C / 55% R.H. 175 micron

For information regarding EHS regulation, please visit our website under downloads "Technical bulletins" TB 7.8 Product Compliance Fasson Offset" and for technical guidance "Technical bulletins" – Offset printing.



FASSON[®] HG White DI-OF FSC[®] Certified

PRODUCT CHARACTERISTICS

Physical properties

Face

Basis weight:	80 g/m ²	ISO 536
Caliper:	78 micron	ISO 534
Tensile:	4.3 kN/m MD / 2.7 kN/m CD	ISO 1924/2
Opacity:	92 %	ISO 2471
Opacity.	72 /0	130 2471

Adhesive

Permanent:	General-purpose water-based permanent adhesive with a high initial tack and
	high adhesion on most common substrates.

Permanent

Adhesion (N/m) (FTM 2 on steel/20 min. bond time)	365
Tack (N) (FTM 9 on st.steel)	10.3
Minimum application temperature	+5
Service temperature range after 24 hrs (°C)	+80
Resistance to cold (°C) ¹⁾ down to	-20

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Backing Crack-Back[®] Plus: One-side-coated bleached kraft paper, with diagonally crush-scored lines, along which the backing will crack cleanly when bent back, allowing easy removal in just two pieces. Lines are spaced just 32 mm apart. Good layflatness ensures first-class printing and finishing. (For optimal functionality take care of the following: minimum label size must be 20 cm². The shortest side of a rectangle or the smallest diameter of an ellipse must be at least 25 mm.)

Basis weight:	86 g/m ²	ISO 536
Caliper:	87 micron	ISO 534

This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see https://www.lecta.com/terms Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel – Lecta under license

from Avery Dennison Corporation and related entities for EMENA only.

